

AO482R ($\geq 76\%$)

2023.04.03

SPECIFICATIONS

▶ Chemical formula:	Al ₂ O ₃
▶ Chemical name:	Aluminium oxide
▶ Apperance:	Porous sintered aluminum oxide
▶ Main characteristics:	High mechanical strength, high temperature resistance, high frequency insulation, high chemical resistance, high heat resistance
▶ Main applications:	Welding nozzle, nozzle for glass fiber manufacturing
▶ Colour:	Pink

MECHANICAL & PHYSICAL CHARACTERISTICS (TYP.)

Density		[g/cm ³]	JIS R 1634	3.6
Water absorption		[%]	JIS C 2141	0.6
Vickers hardness HV9.807N		[GPa]	JIS R 1610	9.0
Flexural strength 3 P.B.		[MPa]	JIS R 1601	120
Compressive strength		[MPa]	JIS R 1608	-
Young's modulus of elasticity		[GPa]	JIS R 1602	160
Poisson's ratio		[ν]	JIS R 1602	0.17
Fracture toughness (SEPB)		[MPa*m ^{0.5}]	JIS R 1607	-
Coefficient of linear thermal expansion	40 - 400 °C			7.1
	40 - 800 °C	[$\times 10^{-6}$ /K]	JIS R 1618	7.5
Thermal conductivity		[W/(m*K)]	JIS R 1611	8
Specific heat capacity		[J/(g*K)]	JIS R 1611	0.75
Thermal shock temperature difference		[°C]	JIS R 1648	320
Dielectric strength		[kV/mm]	JIS C 2141	12
Volume resistivity	20 °C			>10 ¹⁴
	300 °C	[Ω*cm]	JIS C 2141	10 ¹⁰
	500 °C			10 ⁸
Dielectric constant		-	JIS C 2141	8.4
Dielectric loss angle		[$\times 10^{-4}$]	JIS C 2141	180
Loss factor		[$\times 10^{-4}$]	JIS C 2141	1,500

The values are typical material properties and may vary according to products configuration and manufacturing process.
For more details, please feel free to contact us.

KYOCERA Fineceramics Europe GmbH

E-Mail: info@kyocera-fineceramics.de · www.kyocera-fineceramics.de

© 2023 KYOCERA Fineceramics Europe GmbH. We reserve the right to make changes without prior notice.