

SN201B

2023.04.03

SPECIFICATIONS

- ▶ Chemical formula: Si_3N_4
- ▶ Chemical name: Silicon nitride
- ▶ Apperance: Dense sintered silicon nitride
- ▶ Main characteristics: High temperature strength, wear resistant ,excellent thermal shock resistance, light weight
- ▶ Main applications: Anti wear liner, powder equipment, molten metal parts, metal forming tool
- ▶ Colour: Black

MECHANICAL & PHYSICAL CHARACTERISTICS (TYP.)

Density		[g/cm ³]	JIS R 1634	3.2
Water absorption		[%]	JIS C 2141	0
Vickers hardness HV9.807N		[GPa]	JIS R 1610	13.9
Flexural strength 3 P.B.		[MPa]	JIS R 1601	580
Compressive strength		[MPa]	JIS R 1608	-
Young's modulus of elasticity		[GPa]	JIS R 1602	290
Poisson's ratio		[ν]	JIS R 1602	0.28
Fracture toughness (SEPB)		[MPa*m ^{0.5}]	JIS R 1607	4 ~ 5
Coefficient of linear thermal expansion	40 - 400 °C	[$\times 10^{-6}/\text{K}$]	JIS R 1618	2.4
	40 - 800 °C	[$\times 10^{-6}/\text{K}$]		3.2
Thermal conductivity		[W/(m*K)]	JIS R 1611	25
Specific heat capacity		[J/(g*K)]	JIS R 1611	0.64
Thermal shock temperature difference		[°C]	JIS R 1648	550
Dielectric strength		[kV/mm]	JIS C 2141	-
Volume resistivity	20 °C	[$\Omega \cdot \text{cm}$]	JIS C 2141	>10 ¹⁴
	300 °C	[$\Omega \cdot \text{cm}$]		10 ¹²
	500 °C	[$\Omega \cdot \text{cm}$]		10 ¹⁰
Dielectric constant		-	JIS C 2141	-
Dielectric loss angle		[$\times 10^{-4}$]	JIS C 2141	-
Loss factor		[$\times 10^{-4}$]	JIS C 2141	-

The values are typical material properties and may vary according to products configuration and manufacturing process.
For more details, please feel free to contact us.

KYOCERA Fineceramics Europe GmbH

E-Mail: info@kyocera-fineceramics.de · www.kyocera-fineceramics.de

© 2023 KYOCERA Fineceramics Europe GmbH. We reserve the right to make changes without prior notice.